

BLUEONE™ PICKLING PASTE 130

A unique patented, safer-to-use pickling paste!


Many of the processes used for pickling stainless steel lead to the development of hazardous nitric fumes. To improve safety when pickling, we have developed a unique patented low-fuming pickling paste which reduces toxic nitric fumes by 80 %.

Standard applications

Avesta BlueOne™ Pickling Paste 130 is universally, suitable for brush pickling of welds and smaller surfaces on all stainless steel grades.

Features

- » Restores damaged stainless steel surfaces such as weld seams, by removing weld oxides, the underlying chromium-depleted layer and other defects that may cause local corrosion.
- » Improved pickling result, offers a brighter surface with less discolouration than classic products.
- » Unique and covered by a world patent.
- » Higher yield, decreased consumption, thanks to the visible blue colour and its free-flowing consistency which facilitates application. The paste is easy to apply and highly visible.




80% fume reduction compared to standard Pickling Paste.

Avesta BlueOne™ Pickling Paste 130 is unique and covered by a world patent.



Instructions for use




1. Stir or shake the paste before use.



2. Apply the paste with an acid-resistant brush.



3. Typical pickling time for Steel grade 304/316 is 90 min at 10 °C, 45 min at 20 °C and 20 min at 30 °C. The pickling time may vary for the same steel grade, depending on the surface finish and the welding method.



4. Remove pickling residues using a high-pressure water jet, or with a stainless steel brush and then rinse with water. The waste water should be treated before discharge.

Packaging

Avesta BlueOne™ Pickling Paste 130 is supplied in a 2.4 kg polyethylene container supplied in a 4-pack cardboard box, and a 13 kg polyethylene container.

All packing material follows the UN regulations for hazardous goods.

Storage

Avesta BlueOne™ Pickling Paste 130 should be stored indoors at room temperature. Containers must be kept properly closed, in an upright position and inaccessible to unauthorized persons.

The product is perishable and should not be kept in storage longer than necessary. It has a maximum shelf life of two years when stored at room temperature. Exposure to higher temperatures (> 35 °C) may damage the product and reduce the shelf life.

Worker safety

Avesta First Aid Spray 910 (available only on some markets) or Hexafluorine® should be readily available to all who work with pickling to use as a first rinse to decontaminate small acid splashes of pickling paste, followed by Calcium Gluconate Gel or Solution to be used as a first aid to treat the HF acid burn.

Protective clothing. In general, users should wear acid-resistant overalls, gloves and rubber boots. Face visor should be used and, if necessary, suitable respiratory protective devices.

Special conditions may apply from one country to another. Consult our website where updated Safety Data Sheets can be found.

Waste treatment

The waste water produced when pickling contains acids and should be treated with Avesta Neutraliser 502 or with slaked lime to a pH-value of 7 – 10 before discharge.

Heavy metals from stainless steel are precipitated as a sludge, and should be sent for deposition according to local regulations.

Empty containers (HDPE) must be cleaned and can then be recycled according to local regulations.

Other information

For more information, please visit our website: <http://www.vabw-service.com/voestalpine> where you can find Safety Data Sheets and other useful information.



Information given in this brochure may be subject to alteration without notice. Care has been taken to ensure that the contents of this publication are accurate, but voestalpine Böhler Welding Nordic AB and its subsidiary companies do not accept responsibility for errors or for information which is found to be misleading. Suggestions for or descriptions of the end use or application of products or methods of working are for information only and the company and its subsidiaries accept no liability in respect thereof. Before using products supplied or manufactured by the company the customer should satisfy himself of their suitability.